

**BEST FOR
CEILINGS
LEVELLING**

EGALISS

SKIMCOAT FILLER TO LEVEL QUICKLY UNEVEN OR DAMAGED SUBSTRATES



- ▶ **NEW BUILD AND RENOVATION SITES**
- ▶ **ADHERES EVEN ON PAINTED SUBSTRATES**
- ▶ **UP TO 1 CM PER COAT**
- ▶ **OPEN TIME 2 H**
- ▶ **EXTRA WHITE AND FINE**

PURPOSE

Skimcoat Filler in powder form, for interior use, manual application.

SUBSTRATES

EGALISS can be applied on either new or renovated substrates, either unpainted or painted:

- Gypsum plaster, plasterboards, dry wall lining,
- Old painted surfaces,
- Any filler type of Toupret range,
- Cement, concrete, cellular concrete, breeze block,
- Slightly or highly structured surfaces finishes.

OVERCOATING

EGALISS can be coated over by any type of Toupret filler, paints and wall coverings.

Physical and technical FEATURES

EGALISS: Interior filler in powder form, made of selected quarry materials and binder.

- Characterization (NFT 36-005): Family III class 3
- Codification (EN 16566): $G_3S_1V_0W_0A_0C_0R_0$
- Mixing : 45% of water (i.e 0.45 L of water for 1 kg of powder)
- Application thickness: Up to 1 cm in one coat
- Consumption: 1 kg/m²/mm
- Working time: 2 hours
- Second coat: 2 h 30 approximately
- Overcoating: 12 to 24 hours average time
- Colour: White
- Shore hardness: 80
- Adhesion filler/substrates (EN 16566): > 0.5 MPa

USE AND STORAGE CONDITIONS

- Application tool: with surfacing blade or trowel
- Tools cleaning: with water.
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from dampness.

PACKAGING

- Bag of 15 kg.

RECOMMENDATIONS and care for use

- Do not apply **EGALISS** on polystyrene, nor on adhesive coverings nor on exterior substrates.
- Do not apply under a temperature < 8 °C and over > 35 °C nor under an hygrometry rate over 70%.
- Do not apply on overheated surfaces
- Do not apply on damp surfaces
- Do not remix the paste when it begins to set

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- EN 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204): Setting up of wall papers and wall coatings.

HEALTH AND SAFETY

- No danger tag.
- Very low VOC emissions : < 0,02 %.
- Safety data sheets available on www.toupretpro.co.uk or toupret.com.

The data sheet information, especially the guidelines relevant to the application and final use of **EGALISS** are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.
The product is required to be used as per the trade practices rules book and in reference to our recommendations.
The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.
The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).