

WHITE AND FINE

J-MIX

DRY WALL JOINT COMPOUND



- ▶ UP TO 5 MM
- ▶ HIGH ADHESIVE THICKNESS STRENGTH
- ▶ HIGH FILLING POWER
- ▶ EASY SANDING

PURPOSE

Ready to use dry wall joint compound to be used in association with a joint tape, interior use, manual application. Can also be used as finish surface filler.

SUBSTRATES

J-MIX can be applied on any type of plasterboards with thin edges with or without insulating parts and plaster carton boards.

OVERCOATING

J-MIX can be coated with a primer or a surface filler.

Physical and technical FEATURES

- J-MIX: filler in paste form for interior use, made of mineral components and synthetic resin.
- Characterization (NFT 36-005): Family III - Class 2
 - Codification (EN 16566): $G_3S_1V_0W_0A_0C_0R_0$
 - Application thickness: up to 5 mm
 - Consumption: Approx. 300 gr/m²
 - Overcoat: When fully dry (depends on the thickness which has been applied)
 - Colour: White
 - Adhesion filler/substrate (EN 16566): > 0.5 Mpa

USE AND STORAGE CONDITIONS

- Application tool : With smoothing or surfacing blade
- Tools cleaning: with water
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from frost and sun.

PACKAGING

- Bucket of 25 kg

RECOMMENDATIONS and care for use

- Do not apply under a temperature < 8 °C and > 35 °C nor under an hygrometry rate over 70%.
- Do not apply on overheated surfaces
- Do not apply on damp substrates
- Do not apply on polystyrene, nor on wall paper, nor on exterior substrates.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- EN 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204): wall papers and wall coverings processing

HEALTH AND SAFETY

- No danger tag.
- Very low VOC emissions : < 0,02 %
- Safety data sheets available on www.toupretpro.co.uk or toupret.com.

The data sheet information, especially the guidelines relevant to the application and final use of J-MIX are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).