

WOOD REPAIR

WOOD REPAIR FILLER

[**FAST DRYING**]

- ▶ **EASY TO PREPARE, MONOCOMPONENT**
- ▶ **EXCELLENT ADHERENCE**
- ▶ **CAN BE CARVED, SANDED, DRILLED AND PAINTED**
- ▶ **NO THICKNESS LIMIT**

PURPOSE

Filler in powder form, to reconstitute missing wooden parts and repair broken angles. For interior and exterior use. Manual application.

OVERCOATING

WOOD REPAIR can be overcoated by any type of conventional paints, varnishes and stains.

SUBSTRATE

WOOD REPAIR applies on any types of woods, including exotic species, chipboard and plywood.

Physical and technical FEATURES

WOOD REPAIR is a filler in powder form, for interior or exterior use, made of mineral extracts and selected binders.

- Characterization (NFT 36-005): Family IV class 4c
- Codification (NFT 30-608): G₃E₃S₃V₀W₀A₀C₀
- Mixing rate: 30% water (hence 0.3 litre water for 1 kg powder)
- Application thickness: no limitation
- Working time: 30 minutes
- Second coat: once the filler is dry
- Overcoat: 3 HRS average time (after complete drying)
- Colour: wood beige
- Adhesion filler/substrate (NFT 30-608): > 0,8 MPa

USE AND STORAGE CONDITIONS

- Application tools: coating knife, trowel or blade.
- Tools cleaning : with water.
- Preservation: product guaranteed 6 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from humidity.

PACKAGING

- Box of 1 kg



RECOMMENDATIONS and care for use

- Do not apply on polystyrene, nor on damp substrates.
- Do not apply under a temperature < 5 °C and > 35 °C nor under an hygrometry rate over 80%.
- On exterior substrates, Wood Repair is required to be coated over
- On rough (unprepared) wood, it is recommended to apply **TOUPRET WOOD HARDENER** beforehand.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- NFT 30-608: Coating fillers for interior works and/or exterior.
- NFT 36-005: Characterization of paint products.
- French DTU 59.1 (NFP 74-201): Building paint works.

HEALTH AND SAFETY

- No danger tag
- Very low VOC emissions : < 0.1%.
- Safety data sheets available on www.toupretpro.co.uk or toupret.com.

The data sheet information, especially the guidelines relevant to the application and final use of Le **WOOD REPAIR** are provided in good faith and result from the knowledge of the products and experience of **TOUPRET** company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).